

Collected Data Sheet



PONACOM PS Industrial Compounds

Product	Product description	Density	MFI (200°C - 5 kg)	Charpy impact notched Charpy + 23°C	Izod impact strength notched Izod + 23°C	Processing temp. ./. °C
		EN ISO 1183 g/cm ³	EN ISO 1133 g/10 min	EN ISO 179-1/1eA kJ/m ²	EN ISO 180/1 kJ/m ²	
PONACOM 5360 industrial black	medium impact - injection / extrusion	1,05	5 - 8	6 - 7	8	180 - 240
PONACOM 5370 industrial black	high impact - injection / extrusion	1,05	5 - 8	7 - 8	9	180 - 240
PONACOM 5380 industrial black	high impact - injection / extrusion	1,05	5 - 8	8 - 9	10	180 - 240
PONACOM 5470 black	high impact - injection / extrusion	1,05	5 - 8	7 - 8	9	180 - 240
PONACOM 5480 black	high impact - injection / extrusion	1,05	5 - 8	8 - 9	10	180 - 240
PONACOM 5560 deep black	medium impact - injection / extrusion	1,05	5 - 8	6 - 7	8	180 - 240
PONACOM 5570 deep black	high impact - injection / extrusion	1,05	5 - 8	7 - 8	9	180 - 240
PONACOM 5570-10 deep black	high impact - injection	1,05	8 - 12	7 - 8	9	180 - 240

This list contains only a selection of all types. Please send us your request. We will send our offer.